

## LIONCAT 25-M

### 产品成分:

阳离子表面油，为天然高熔点蜡及精制牛蹄油的混合物。

### 技术指标:

|             |  |
|-------------|--|
| 外观          | 白色膏状   |
| 有效物含量       | 64% ( $\pm 2$ )  |
| 离子性         | 阳离子  |
| 密度 (磅/加仑)   | 8.0 ( $\pm 0.2$ )  |
| pH (10% 溶液) | 4.0 – 5.0  |
| 储存稳定性       | 室温下, 1 年。<br>最佳储存温度为 15°C -30°C。                               |
| 凝固/融化稳定性    | 对低温敏感。要求储藏温度不低于 5°C。   |
| 耐光性         | 好  |
| 耐电解质性能      | 好  |
| 乳化性         | 使用前乳化。<br>易溶于热水。<br>与热水以 1:1 均匀混合, 30°C -60°C 时, 与水以 1:4 进行乳化。 |

### 主要性能:

Lioncat 25-M 通常用做表面油，以获得丰富、蜡感且光滑的表面手感。在干燥中也作为离板剂使用。

- 是一支优异的表面油，赋予成革丰富、光滑的手感。
- 干燥中优异的离板性能。
- 良好的表面润滑性。
- 产生表面封闭效果，利于后继油蜡涂饰。
- 赋予摔软革柔软手感。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

|                  |                          |
|------------------|--------------------------|
| 以削匀蓝革重量计算<br>表面油 | 1.0% - 2.0% Lioncat 25M  |
| 离板剂              | 0.75% - 2.0% Lioncat 25M |
| 摔软碎石纹革           | 1.0% - 2.0% Lioncat 25M  |
| 家具革              | 1.0% - 2.0% Lioncat 25M  |
| 全粒面纳帕革           | 1.0% - 2.0% Lioncat 25M  |
| 绵羊、山羊、小牛革        | 1.0% - 2.0% Lioncat 25M  |
| 反绒革、正绒革          | 1.0% - 2.0% Lioncat 25M  |
| 鹿皮               | 1.0% - 2.0 % Lioncat 25M |
| 油蜡革              | 2.0% - 4.0% Lioncat 25-M |

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.