

## LIONCAT CF-32

### 产品成分:

是一支浓缩产品，主要成分是经阳离子乳化剂乳化的天然油和合成油的混合物。

### 技术指标

外观	深棕色油状物
有效物含量	100%
电荷	阳离子
密度 (磅/加仑)	7.8 (± 0.2)
pH (10% 溶液)	4.5 – 5.5
储存稳定性	室温下，1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固，使用前加热到 25°C -30°C，并充分混合至均匀。
耐光性	较好
耐电解质性能	好
乳化性	50°C - 70°C 时，以 1:6 乳化。 加入转鼓前充分混合。

### 主要性能:

Lioncat CF-32 是一支阳离子表面油，可单独用于工序结束前以获得光滑、蜡感、及丰富的表面手感。

- 赋予革面丰富且有拖曳感的手感。
- 改善粒面强度及表面润滑性。
- 贴板干燥中用做离板剂。
- 低表面渗透。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算  
离板剂

工序末换水后加 0.5% - 2.0% Lioncat  
CF-32, 转 10 - 15'。

表面油

工序末换水后加 2-4% Lioncat CF-32, 转  
10 - 15'。

加脂油

工序末换水后加 6-8% Lioncat CF-32, 转  
30 - 45'。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.