

LIONCAT CF-88

产品成分:

是一支浓缩产品，主要成分是经阳离子乳化剂乳化的天然油蜡和合成油蜡的混合物。

技术指标:

外观	棕色固体
有效物含量	100% (± 2)
电荷	阳离子
密度 (磅/加仑)	7.2 (± 0.2)
pH (10% 溶液)	4.0 – 5.0
储存稳定性	室温下，1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。
耐光性	较好
耐电解质性能	好
乳化性	使用前融化，温度 70°C。 65°C -70°C 时，以 1:4 乳化。 加入转鼓前充分混合。

主要性能:

Lioncat CF-88 用做单一组分阳离子填充蜡。用于制作帖板干燥或真空干燥的全粒面及修面多脂或半加脂革。

- 优异的单一组分变色蜡。
- 清晰明亮的变色效应，底色少。
- 磨革性好。
- 乳化性优异，分布均匀。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算
变色摔软碎石纹革

8-10% Lionsoft SF-1400, 再加 6-8%
Lioncat CF-88

变色革

8-16% Lioncat CF-88

半加脂靴用革

4-8% Lioncat CF-88

变色家具革

12-14% Lionsoft SF-1400 和
6-8% Lioncat CF-88

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.