

# LIONCRYL AR-79

## 产品成分:

丙烯酸合成鞣剂

## 技术指标:

外观	浅黄色液体
有效物含量	31 - 33%
电荷	阴离子
密度(磅/加仑)	8.0 (± 0.2)
pH (10% 溶液)	4.0 - 4.6
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -30°C, 并充分混合至均匀。
耐光性	好
耐电解质性能	好
乳化性	使用前乳化。 易溶于热水。 40°C -60°C 时, 与水以 1:4 进行乳 化。

## 主要性能:

Lioncryl AR-79 赋予皮革优异的柔软度, 并能提高粒面强度。适用于柔软、丰满的各类皮革。

- 小分子量, 渗透性优异。
- 可生产柔软度、坚实度不同的各类皮革。
- 粒面紧实、丰满、平坦。
- 密度低。
- 优异的丰满度及圆润度。
- 良好的匀染性。
- 优异的耐光性。
- 低雾化性。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算 中和	1 - 2 % Lioncryl AR-79
摔软碎石纹革	2 - 8% Lioncryl AR-79
家具革	4 - 6% Lioncryl AR-79
全粒面纳帕革	2 - 4% Lioncryl AR-48 配合 4 - 8% Lioncryl AR-79
绵羊、山羊、小牛革	4 - 8% Lioncryl AR-79

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.