

# LIONOL SC-L-35

## 产品成分:

浓缩硫酸化油、氧化鱼油、石油的混合物。

## 技术指标:

外观	深色液体/膏状
有效物含量	88% (± 2)
电荷	阴离子
密度(磅/加仑)	8.0 (± 0.2)
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -30°C, 并充分混合至均匀。
耐光性	好
耐电解质性能	较好
乳化性	使用前乳化。 易溶于热水。 50°C -60°C 时, 与水以 1:4 进行乳 化。

## 主要性能:

Lionol SC-L-35 通常用于生产紧实、丰满粒面的鞋面革、靴用革、半加脂革、及纳帕革, 并作为主加脂剂用于变色革的生产。

- 丰富手感及蜡感。
- 粒面圆润、丰满且紧实。
- 颜色清晰明亮。
- 有助于填充蜡的渗透。
- 优异的粒面润滑效果。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算 变色革	5% Lionol SC-L-35 和 5% Lionwax 38-DW
半加脂靴用革	5% Lionol SC-L-35 和 3% Lionwax 38-DW
全粒面鞋面革	3% Lionol SC-L-35 和 5% Lioncat SG-3
摔软碎石纹加脂革	8-10% Lionsoft SF-1400 配合复鞣剂 4% Lioncat SC-L-35 和 4% Lionwax 38-DW
加脂革	3%-5% Lionol SC-L-35, 再加 4%-8% Lioncat 49
加脂休闲鞋面革	8%- 10% Lionol SC-L-35, 表面加 2%-4% Lioncat 49 或 Lioncat CF-12
全粒面纳帕革	4% Lionsoft SF-1400 和 2% Lionol LN-151 和 3% Lionol SC-L-35

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.