

## LIONPHOS P-76

### 产品成分:

多用途磷酸酯合成加脂剂。

### 技术指标:

外观	清澈灰白色液体
有效物含量	60% ( $\pm 2$ )
电荷	阴离子
密度(磅/加仑)	8.2 ( $\pm 0.2$ )
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C- 35°C, 并充分混合至均匀。
耐光性	好
耐热性	好
耐电解质性能	优异

### 主要性能:

Lionphos P-76 是一支合成加脂剂, 可单独使用, 也可配合其它加脂剂一同使用, 起到以下作用:

- 增加加脂剂的渗透。
- 提高对硬水的稳定性。
- 帮助铬鞣革的回湿。
- 提高其它加脂剂的使用效果。
- 赋予成革优异的柔软度。
- 提高对电解质的稳定性。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算。

预加脂	1.0 – 2.0 % Lionphos P-76 于中和
复鞣	1.0 – 2.0% Lionphos P-76 于铬复鞣
摔纹革	4.0 – 6.0 % Lionphos P-76 和 4.0 – 6.0 % Lionsoft SN-230
全粒面纳帕革	2.0 – 4.0 % Lionphos P-76 和 2.0 – 4.0 % Lionol AF-15 和 4.0 – 6.0 % Lionsoft SN-230
家具革	3.0 – 4.0 % Lionphos P-76 和 4.0 – 6.0 % Lionsoft SV-348 和 4.0 – 6.0 % Lionsoft SN-230
加脂助剂	2.0 – 4.0 % Lionphos P-76 配合主加脂剂

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.