

LIONPROOF FLX

产品成分:

硅树脂/聚合物乳液，用于防水革生产。为得到最佳效果，应用后应以金属盐固定。

技术指标:

外观	白色液体/膏状物
有效物含量	58% – 62%
电荷	阴离子
密度(磅/加仑)	7.5 – 8.5
pH (10% 溶液)	7.0 – 9.0
储存稳定性	室温下，1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温敏感。 储藏温度不低于 5°C。
耐光性	好
耐电解质性能	好
乳化性	使用前乳化。 易溶于热水。 与热水以 1:1 混合至均匀，再与 30°C-60°C 的水以 1:4 乳化。

主要性能:

Lionproof FLX 通常配合其他疏水产品一同用于防水革生产系统，赋予皮革防水性能，并提高革动态防水哇次数。

- 用于铬鞣革的防水加脂剂。
- 赋予皮革高动态防水哇次数。
- 赋予皮革低吸水性。
- 可用于染色革或白色革。
- 作为表面油使用可提高皮革表面的抗水性。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算
表面油

2.0% - 4.0% Lionproof FLX
之后加

防水鞋面革

2.0% - 4.0%金属盐

4.0% - 6.0% Lionproof SE 和

4.0% - 6.0% Lionproof FLX
之后加

1.0% - 2.0% Lionproof FWP

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.