

LIONSOFT LN-55-A

产品成分:

重亚硫酸化天然油、卵磷脂以及优质乳化剂的混合物。

技术指标:

外观	黄色液体
有效物含量	50% (± 2)
电荷	阴离子
密度(磅/加仑)	8.2 (± 0.2)
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -30°C, 并充分混合至均匀。
耐光性	好
耐电解质性能	好
乳化性	使用前乳化。 易溶于热水。 50°C -60°C 时, 与水以 1:4 进行乳 化。

主要性能:

Lionsoft LN-55-A 通常用于制作软革, 如家具革、服装革、以及摔软革。

- 优异的渗透油, 以及加脂剂的配套产品。
- 优异的稳定性, 铬复鞣及硬水环境下都稳定。
- 赋予成革优异的抗张强度。
- 有助于提高其它加脂剂的渗透及柔软效果。
- 优异的柔软度、光滑度及丰富的手感。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算。

预加脂

2-4% Lionsoft LN-55-A 于中和

复鞣

2-4% Lionsoft LN-55-A 于铬复鞣

纳帕服装革

6-10% Lionsoft LN-55-A

绵羊、山羊、小牛革

6% Lionsoft LN-55-A 和
4-6% Lionol AF-15

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.