

## LIONSOFT SF-1400

### 产品成分:

是一支中度氧化的重亚硫酸化鱼油。

### 技术指标:

外观	琥珀色液体
有效物含量	84% ( $\pm 2$ )
电荷	阴离子
密度(磅/加仑)	8.0 ( $\pm 0.2$ )
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -30°C, 并充分混合至均匀。
耐光性	好
耐电解质性能	很好
乳化性	使用前乳化。 易溶于热水。 30°C -60°C 时, 与水以 1:4 进行乳 化。

### 主要性能:

Lionsoft SF-1400 通常用于制作软革, 如家具革、服装革、及摔软鞋面革。

- 优异的渗透油, 可配合其它加脂剂一同使用。
- 优异的稳定性, 铬复鞣及硬水环境下都稳定。
- 赋予成革优异的抗张强度。
- 在复鞣中使用有助于提高其它加脂剂的渗透及柔软效果。
- 相同产品但有效物含量不同的有: Lionsoft SF-1200 (88%), Lionsoft SF-100 (80%)。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量/相应皮重计算。

浸酸	0.5% - 1.0% Lionsoft SF-1400
预加脂	1-2% 于中和
复鞣	1-2% Lionsoft SF-1400 于铬复鞣 2-4% Lionsoft SF-1400 于植复鞣
摔软碎石粒纹革	6-8% Lionsoft SF-1400 和 6-8% Lionol SF-50-P
家具革	12-14% Lionsoft SF-1400 和 6-8% Lionol 96-S
全粒面纳帕革	4% Lionsoft SF-1400 和 2% Lionol LN-151 和 3% Lionol SC-L-35
绵羊、山羊、小牛革	3% Lionsoft SF-1400 和 4-6% Lionol AF-15

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.