

LIONSFT SF-50-P

产品成分:

中度氧化的重亚硫酸化鱼油、乳化剂、及中性润滑油。

技术指标:

外观	琥珀色液体
有效物含量	92% (± 2)
电荷	阴离子
密度(磅/加仑)	8.0 (± 0.2)
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -30°C, 并充分混合至均匀。
耐光性	好
耐电解质性能	很好
乳化性	使用前乳化。 易溶于热水。 30°C -60°C 时, 与水以 1:4 进行乳 化。

主要性能:

Lionsoft SF-50-P 通常用于制作软革, 如家具革、服装革、及摔软鞋面革。

- 优异的渗透油, 以及加脂剂的配套产品。
- 优异的稳定性, 铬复鞣及硬水环境下都稳定。
- 赋予成革优异的抗张强度。
- 有助于提高其它加脂剂的渗透及柔软效果。
- 良好的耐热及耐光性。
- 优异的柔软度及固定效果。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量/相应皮重计算。

浸酸	0.5% - 1.0% Lionsoft SF-50-P
预加脂	1 - 2% Lionsoft SF-50-P
复鞣	1 - 2% Lionsoft SF-50-P 于铬复鞣 2 - 4% Lionsoft SF-50-P 于植复鞣
摔纹革	8 - 10% Lionsoft SN-230 和 4 - 6% Lionsoft SF-50-P
家具革	12 - 14% Lionsoft SF-1400 和 4 - 6% Lionsoft SF-50-P
服装革	8 - 12% Lionsoft SN-873 和 6 - 8% Lionsoft SF-50-P

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.