

LIONSOF SV-348

产品成分:

中度氧化的重亚硫酸化植物油与乳化剂的混合物。

技术指标:

外观	黄色液体
有效物含量	65% (± 2)
电荷	阴离子
密度(磅/加仑)	8.4 (± 0.2)
pH (10% 溶液)	6.0 – 8.0
储存稳定性	室温下, 1 年。 最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。 若发生凝固, 使用前加热到 25°C -35°C, 并充分混合至均匀。
耐光性	好
耐热性	很好
耐电解质性能	很好

主要性能:

Lionsoft SV-348 通常用于制作软革, 如家具革、服装革、包革、纳帕革、以及鞋面革。

- 优异的渗透油, 及加脂剂配套产品。
- 良好的稳定性, 铬复鞣及硬水环境下都稳定。
- 有助于提高其它加脂剂的渗透及柔软效果。
- 优异的柔软度及低密度。
- 优异的耐热及耐光性。
- 低雾化值。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算。

预加脂	1 - 2% Lionsoft SV-348 于中和
复鞣	1 - 2% Lionsoft SV-348 于铬复鞣 2 - 4% Lionsoft SV-348 于植复鞣
摔纹革	8 - 12% Lionsoft SV-348
汽车革	4 - 6% Lionsoft SV-348 4 - 6% Lionsoft SV-873
家具革	2 - 4% Lionsoft SF-1400 于复鞣 10 - 16% Lionsoft SV-348
绵羊、山羊、小牛革	2 - 4% Lionsoft SV-348 和 4 - 6% Lionol AF-15

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.