

## LIONWAX 38-DW

### 产品成分:

深色填充材料，矿物蜡和油脂的混合产品。

### 技术指标:

外观	深色蜡
有效物含量	100%
熔点	48 - 52°C
电荷	无
密度(磅/加仑)	6.8 (± 0.2)
溶解性	不溶于水
储存稳定性	最佳储存温度为 15°C -30°C。
凝固/融化稳定性	对低温不敏感。
耐光性	好
乳化性	不溶于水。 使用前熔化，温度 70°C。 乳化后加入加脂剂。

### 主要性能:

Lionwax 38-DW 是一支不溶于水的填充蜡，可配合其它产品一同使用于加脂革、半加脂革、或变色效应革的水场加脂填充工序。

- 赋予皮革良好的填充和坚实效果。
- 不会在革面形成油霜。
- 颜色清晰明亮且均匀。
- 优异的变色效应。
- 磨革性好。

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.

应用说明:

以削匀蓝革重量计算。

变色效应革	5% Lionol SC-L-35 和 5% Lionwax 38-DW
阳离子加脂革	5% Lioncat CF-12 和 5% Lionwax 38-DW
半加脂靴用革	5% Lionol SC-L-35 和 3% Lionwax 38-DW
摔软碎石纹加脂革	8-10% Lionsoft SF-1400 于复鞣 4% Lioncat SC-L-35 和 4% Lionwax 38-DW
变色家具革	12-14% Lionsoft SF-1400 和 4% Lioncat CF-12 和 4% Lionwax 38-DW
变色革	5% Lionol SC-L-35 和 5% Lionwax 38-DW

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.