

COMPOSITION:

For the removal and further prevention of mold, mildew and spew.

SPECIFICATIONS

Appearance	Dark Liquid
Activity	100%
Charge	Anionic
Density (Lb/Gal)	6.8 (± 0.2)
pH (10% Solution)	4.0 – 6.0
Storage Stability	1 Year at Room Temperature Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not Sensitive to Freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Electrolyte Stability	N/A
Emulsification	Not Soluble in Water.

KEY PROPERTIES:

- Vitasan 33 is made specifically for use in the finish process.
- Aids in the prevention of mold and fatty spews.
- May not prevent mold. Mildew, or spew from leather substance below and should not be considered a replacement for Vitasan 10 in the wet end.

APPLICATIONS:

Vitasan 33 can be added to and applied with a finish coat. It is necessary to experiment with the mixing procedure to ensure stability.

Vitasan 33 can be applied to crusted or finished leathers by swabbing, spray, or oiling-off machine. It can be applied to the grain, flesh, or both depending upon the condition of the leather.

It is most effective if the leather is preheated, sprayed, and hung to dry overnight.

Normal requirement is 4-6 gr./sq. ft. as is. Product should not be diluted!