

SOFTOIL LP-60

COMPOSITION:

Softoil LP-60 is a high grade sulphonated fish oil.

SPECIFICATIONS

| | |
|-----------------------|---|
| Appearance | Amber Liquid |
| Activity | 58 – 62 % |
| Charge | Anionic |
| Density (Lb/Gal) | 8.3 (± 0.2) |
| pH (10% Solution) | 6.0 – 7.0 |
| Storage Stability | 1 Year at room temperature Optimum storage temperature is between 15°C and 30°C. |
| Freeze/Thaw Stability | Not Sensitive to Freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous. |
| Lightfastness | Good |
| Electrolyte Stability | Very Good |
| Emulsification | Mix before use. Readily soluble in warm water. Emulsify 1:4 at 30°C to 60°C |

KEY PROPERTIS:

Softoil LP-60 is a specially developed economical fish oil to produce leathers where a high degree of softness is required. Leathers produced with Softoil LP-60 will retain softness for longer periods of time.

- A highly penetrating oil and co-product with other anionic fatliquors.
- Good lightfastness properties.
- Excellent electrolyte stability in Chrome retanning and hard water applications.
- Imparts excellent tensile strength.
- Aids in penetration and softening action of other fatliquors when used in retan.

APPLICATIONS:

Recommended usage is 2% to 14% on Blue shaved weight.

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.