

# MARDOL 4051-B



## COMPOSITION:

A blended fatliquor based on bisulfited, sulfated and natural raw oils.

## SPECIFICATIONS

Appearance	Amber Liquid
Activity	82% ( $\pm 2$ )
Charge	Anionic
Density (Lb/Gal)	8.0 ( $\pm 0.2$ )
pH (10% Solution)	6.0 – 8.0
Storage Stability	1 Year at Room Temperature Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not Sensitive to Freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Fair
Electrolyte Stability	Fair
Emulsification	Mix before use. Readily soluble in warm water. Emulsify 1:4 at 50°C to 60°C

## KEY PROPERTIES:

Mardol 4051-B is designed for making drum tanned vegetable leathers where grain lubrication is required.

- Full, Round Temper.
- Excellent Grain Lubrication
- Good Softness Without Looseness
- Heavy Vegetable Leather Fatliquor

## APPLICATIONS:

Recommended use at 4% to 8%