



MARDOL BS-240

COMPOSITION:

A medium blown, bisulfited fish oil, sulfated fish oil and neutral lubricating oils.

SPECIFICATIONS

Appearance	Amber Liquid
Activity	76% (± 2)
Charge	Anionic
Density (Lb/Gal)	8.0 (± 0.2)
pH (10% Solution)	6.0 – 8.0
Storage Stability	1 Year at Room Temperature Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not Sensitive to Freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Fair
Electrolyte Stability	Good
Emulsification	Mix before use. Readily soluble in warm water. Emulsify 1:4 at 30°C to 60°C

KEY PROPERTIES:

Mardol BS-240 is normally used in making soft leathers such as glove, garment, and milled shoe upper leathers

- An excellent penetrating oil and single fatliquor.
- Imparts excellent tensile strength.
- Aids in penetration and softening action of other fatliquors.
- Excellent softness and fixation.

APPLICATIONS:

Recommended usage is 4% to 16%