

		TEST :
Type of Leather:	AUTOMOTIVE CRUST	Date: 2010
Material:	USA Cowhide	Thickness: 1.0-1.2 mm
Percentages based on:	BLUE SHAVED WEIGHT	

OPERATION	PRODUCTS	TEMP °C	%	PREP	TIME (MIN)	CONTROLS	REMARKS
WASH	H2O	40	300		10		DRAIN
NEUT.	H2O	40	100				
	LIONSOFT SF1200-M		3.0		20		
ADD	SODIUM FORMATE		2.0				
	LIONTAN 15		1.5		40		
ADD	SODIUM BICARB		1.0		40	pH	
	RELUGAN® DLF		2.0		40		DRAIN
WASH	H2O	30	300		10		DRAIN
RETAN	H2O	30	100				
	BASYNTAN® WL		6.0				
	TARA POWDER		6.0		45		
ADD	LUGANIL® BLACK NT		4.0		60		
ACID	H2O	60	100				
	FORMIC		1.5		15	pH	DRAIN
WASH	H2O	60	300		10		DRAIN
FAT	H2O	60	100				
	LIONSOFT SF1200-M		9.0		60		
ADD	LIONCRYL AR-48N		2.0		30		
ACID	FORMIC		1.0		15	pH	DRAIN
TOP DYE	H2O	60	150				
	LUGANIL® BLACK NT		1.5		20		
ACID	FORMIC		1.0		25		DRAIN
WASH	H2O	25	300		2X10		PULL
	HORSE						
	SET						
	WET TOGGLE						
	STAKE						