

Tannin™ Has It.

LIONCRYL AR-48-N

tannincorp.com

COMPOSITION

An acrylic polymeric resin.

SPECIFICATIONS

Appearance	Light yellow liquid
Activity	29-31%
Charge	Anionic
Density (Lb/Gal)	8.2 (± 0.2)
pH (10% Solution)	5.5 - 6.5
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Electrolyte Stability	Good
Emulsification	Mix before use. Readily soluble in warm water. Emulsify 1:4 at 40°C to 60°C.

KEY PROPERTIES

LIONCRYL AR-48-N is an excellent, all-purpose acrylic syntan for use in making numerous types of leathers where a round handle and tight grain are required. Leathers produced using **LIONCRYL AR-48-N** exhibit excellent softness and produce leathers with a low density and fluffy feel. This versatile product is an excellent choice for use in all types of milled, soft leathers.

- Round, well-filled handle
- Tight, full grain
- Excellent softness with low density; excellent for all milled leathers
- Excellent heat and light resistance; good pH stability
- Low fogging

APPLICATIONS

Recommended usage is 4% to 6% on Blue shaved weight.



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx