

Tannin™ Has It.

LIONSOF SN-225

tannincorp.com

COMPOSITION

A medium blown, bisulfited neatsfoot oil blended with sulfated synthetic and neutral oils.

SPECIFICATIONS

Appearance	Amber liquid
Activity	65% (± 2)
Charge	Anionic
Density (Lb/Gal)	8.0 (± 0.2)
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Very Good
Heatfastness	Very Good
Electrolyte Stability	Very Good

KEY PROPERTIES

LIONSOF SN-225 is normally used in making soft leathers such as upholstery, garment, bag, nappa, shoe upper leathers, and deerskin.

- An excellent penetrating oil
- Good stability in Chrome retanning and hard water applications
- Imparts excellent tensile strength
- Aids in penetration and softening action of other fatliquors
- Excellent resistance to heat and light
- Round full handle

APPLICATIONS

Recommended usage is 2% to 12% on Blue shaved weight.



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx