

# Tannin™ Has It.

## LIONSOF SV-348

[tannincorp.com](http://tannincorp.com)

### COMPOSITION

A medium blown, bisulfited vegetable oil blended with an added emulsification system.

### SPECIFICATIONS

Appearance	Yellow liquid
Activity	65% ( $\pm 2$ )
Charge	Anionic
Density (Lb/Gal)	8.4 ( $\pm 0.2$ )
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Heatfastness	Very Good
Electrolyte Stability	Very Good

### KEY PROPERTIES

**LIONSOF SV-348** is normally used in making soft leathers such as upholstery, garment, bag, nappa, and shoe upper leathers.

- An excellent penetrating oil and co-product with other fatliquors.
- Good stability in Chrome retanning and hard water applications.
- Aids in penetration and softening action of other fatliquors.
- Excellent softness with low density.
- Excellent resistance to heat and light.
- Low fogging.

### APPLICATIONS

Recommended usage is 2% to 12% on Blue shaved weight.



Tannin Corporation  
65 Walnut Street  
Peabody, MA 01960, USA  
Phone: +1.978.532.4010  
Fax: +1.978.532.5536  
[sales@tannincorp.com](mailto:sales@tannincorp.com)

Tannin Mexico S.A. de C.V.  
Blvd. San Crispin 130  
Fracc. Ind. San Crispin  
Leon, Gto. 37527, Mexico  
teléfono: +52.477.770.9499  
[tanninmex@terra.com.mx](mailto:tanninmex@terra.com.mx)