



MARDEN-WILD CORPORATION

MARDOL BN-365

COMPOSITION

A medium-blown, bisulfited animal oil.

SPECIFICATIONS

Appearance	Yellow liquid
Activity	84% (± 2)
Charge	Anionic
Density (Lb/Gal)	8.0 (± 0.2)
pH (10% Solution)	6.0 – 8.0
Storage Stability	One year at room temperature. Optimum storage temperature is between 15°C and 30°C.
Freeze/Thaw Stability	Not sensitive to freezing. After freezing heat to 25°C to 30°C and mix well until homogeneous.
Lightfastness	Good
Heatfastness	Very Good
Electrolyte Stability	Very Good

KEY PROPERTIES

MARDOL BS-365 is normally used in making soft leathers such as upholstery, garment, bag, nappa, and shoe-upper leathers.

- An excellent penetrating oil and co-product with other fatliquors
- Good stability in Chrome retanning and hard water applications
- Imparts excellent tensile strength
- Aids in penetration and softening action of other fatliquors
- Excellent filling properties with a soft, tight handle

APPLICATIONS

Recommended usage at 2% - 12%.

tannincorp.com



Tannin Corporation
65 Walnut Street
Peabody, MA 01960, USA
Phone: +1.978.532.4010
Fax: +1.978.532.5536
sales@tannincorp.com

Tannin Mexico S.A. de C.V.
Blvd. San Crispin 130
Fracc. Ind. San Crispin
Leon, Gto. 37527, Mexico
teléfono: +52.477.770.9499
tanninmex@terra.com.mx

The Supplier makes no warranty of any kind, expressed or implied, concerning this product or its use. The user assumes all risk of use or handling, regardless of whether the same is in accordance with the direction or suggestion of the supplier.